



試驗報告 TEST REPORT
食品實驗室-台中 FOOD LAB-TAICHUNG

佑松國際企業有限公司
彰化縣花壇鄉灣東村灣東路195巷46號

報告編號 : RM / 2009 / 60053-1
報告頁數 : 1 之 1
報告日期 : 2009/07/06

以下貨品係由客戶送樣，且由客戶聲稱並經客戶確認資料如下：

產品名稱 : 綠的仙屋-硅藻王、OW-志硅藻君
採(送)樣廠商 : 佑松國際企業有限公司
生產或供應廠商 : 日本一志公司
原產國 : 日本
收樣日期 : 2009/06/05
測試日期 : 2009/06/06

測試項目及方法 :

JIS Z2911-2000 : 黑麴黴菌-ATCC 9642
桔青黴菌- ATCC 11797
出芽短梗黴菌-ATCC 15233
綠黏帚黴菌-ATCC 9645
芽枝狀枝孢黴菌-IFO 6348

測試時間 : 25°C 培養 7天

判斷方式 :


等級	樣品生長情形
0	沒有滋生黴菌
1	黴菌滋生面積不超過1/3
2	黴菌滋生面積超過1/3

測試結果 :

菌種在樣品上生長狀況及等級。

樣品生長情形	等級
沒有滋生黴菌	0

---oOo---



Unless otherwise stated the results shown in this test report refer only to the sample(s) tested. This test report cannot be reproduced, except in full, without prior written permission of the Company. 除非另有說明，此報告結果僅對測試之樣品負責。本報告未經本公司書面許可，不可部份複製。

This Test Report is issued by the Company under its General Conditions of Service printed overleaf or available on request and accessible at http://www.sgs.com/terms_and_conditions.htm. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this Test Report is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

TW 7371324

經濟部標準檢驗局試驗報告

報告號碼: 90308002645-01
申請者: 佑松國際企業有限公司
品名: 綠的仙屋-硅藻土
規格: 30公分x35公分x55公分
型號: (空白)
受理日期: 98年06月08日

頁次: 共2頁, 第2頁

完成日期: 98年10月27日

試驗項目	試驗結果
脫臭試驗	
甲醛	
第0分鐘	81.1ppm
24小時後	63.2ppm
甲苯	
第0分鐘	85.4ppm
24小時後	76.8ppm
氨	
第0分鐘	95.7ppm
24小時後	58.3ppm

試驗說明:

1. 脫臭試驗乙項, 依委託者指定試驗條件試驗, 試驗方法如下: 委託者提供內部尺寸長34cmx寬28cmx高54cm之壓克力箱, 箱內的四面內壁及內底均已自行塗佈塗層, 委託者指定以此壓克力箱作為試體。箱頂用壓克力板加蓋密封後, 由箱頂預留的取樣口注入58公升濃度80ppm到100ppm之試驗氣體, 檢測第0分鐘和24小時後的濃度變化。
2. 依申請者98年10月23日申請書, 原品名「壓克力箱」變更為「綠的仙屋-硅藻土」。
3. 本報告如有任何疑問, 請洽詢技術開發科。(電話: 02-23431857)